


**Model:** AC4 STYLE 1L CALM  
**Codes:** 100199495 - L167012869  
**Group:** G-204  
**Format:** 19,05X126,1X0,7  
**Thickness:** 7 mm



### COMPOSITION



	Size	Material	Type of material
Layer 1	0.2	Melamine	Aminoplastic thermosetting resins
Layer 2	0.1	Decorative paper	
Layer 3	6.6	HDF	High-density Fiber Board and water-repellent glues
Layer 4	0.1	Contracara	Hojas de papel kraft impregnadas con resinas fenólicas

### CERTIFICATIONS

Carb certification	CARB: Phase II compliant
--------------------	--------------------------

### FEATURES

-  Imitates the surface of wood
-  Quality product made with selected raw materials, guaranteeing its full residential use for 20 years in the AC4 and AC5 models for private use
-  Format where only one board has been used to finish the entire base surface
-  PanEuropean Forest Certification that guarantees to consumers the origin of the products from sustainably managed forests
-  23. Intensive residential
-  Abrasion-resistance level as per Standard UNE-EN 13329
-  Installation system where gluing the boards to the floor is not necessary. They are installed on a foam and joined together
-  Quality product made with selected raw materials, guaranteeing its full use for 5 years in the AC5 models for public use
-  Is suitable for installing on water radiant heating
-  Safety and joint durability are the main features of this easy installation system that guarantees the elimination of gaps between boards throughout the floor's lifetime. The pressure exerted between boards reinforces the union and prevents it from being carried out incorrectly.
-  32. General commercial

### DIMENSIONAL FEATURES

Item thickness	≤0.50 mm	EN 13329*
Length of face	≤0.50 mm	EN 13329*
Width of face	≤0.20 mm	EN 13329*
Squareness of the item (q)	≤0.20 mm	EN 13329*
Straightness of face	≤0.30 mm/m	EN 13329*
Flatness of item (f)	fw,Cóncavo≤0.50% fw,Convexo≤1%/fl,Cóncavo≤0.15% fl,Convexo≤0.20%	EN 13329*
Joint between items	≤0.20 mm	EN 13329*
Difference in height among items	≤0.15 mm	EN 13329*
Dimensional variations related to changes in relative moisture	≤0.90 mm	EN 13329*
Uv light fastness	7	EN 438-2,16*
Punching	No visible changes	EN 433*
Surface stripping	≥1.00 N/mm2	EN 13329 Anexo D*

### LABORATORY TESTS

Resistance to abrasion	AC4	UNE EN 13329:2000*
Impact resistance	IC2	UNE EN 13329*
Resistance to staining	Grado 5 (G 1 y 2) y Grado 4 (G 3)	EN 438*
Resistance to cigarette burns	4	EN 438*
Furniture leg effect	No damage	EN 424*
Castor chair effect	No damage	EN 425*
Swelling in thickness	≤18%	UNE-EN 13329*
Dimensional stability	Max≤0.15 mm	EN 13329*
Formaldehyde emissions	E1	EN 717*
Slip resistance (cls)	Clase DS	EN 14041*
Tensile strength of joints	>1.0 N/mm2	EN 13329*
Fire resistance	Efl-s1	EN 13501*
Evaluation of propensity to accumulation of electrostatic charges	≤2 kV	EN 14041*
Heat resistance	R=0.056 m2 K/W	ISO 8302-1991*
Swelling in thickness	≤18%	ASTM D 1037*
Slip resistance (dcof)	Class DS:≥0.30	EN 13893*
Critical radiant flux	Cfl	EN ISO 9239-1*
Smoke density (burning)	s1	EN 13501-1*
Density of the board	890 ±5 KG/M3	UNE EN 323*

### PACKING

Boxes	2.4022 M2/CS	
Pallets	115.3058 M2/PAL	
Units	0.2402 M2/ST	
Sale unit	M2	
Base unit	ST	
Net weight	6.6647 KG/M2	
Gross weight	6.8562 KG/M2	

### SPECIAL PIECES

SAP	KEA	Description	Group	Boxes	Pallet	Units	SKU	Basic Unit	Net weight	Gross weight
100115889	L167011910	IGUALACION STYLE CALM 4X270X1	G-155	20 ST/CS	1000 ST/PAL	9 ST/M2	ST	ST		
100176745	L167012678	MAMPERLAN AC4 STYLE 1L CALM 120X7X3	G-163	2 ST/CS	200 ST/PAL	11 ST/M2	ST	ST	1 KG/ST	1 KG/ST
100115900	L167011919	TRANSICION STYLE CALM 4X270X1	G-155	20 ST/CS	1000 ST/PAL	92 ST/M2	ST	ST		
100174157	L167012663	ZOCALO STYLE CALM 8X220X1,5	G-107	14 ST/CS	560 ST/PAL	5 ST/M2	ST	ST	1 KG/ST	1 KG/ST