

Model: TORTONA 1L FONTE

Codes: 100238598 - L165004323

Group: G-235

Format: 120X14,5X1,4


Thickness: 14 mm



ADDITIONAL NOTES

Este material puede presentar algunas piezas con albura. Por un mejor aprovechamiento de la madera, cualquier pedido de esta referencia puede contener un porcentaje de medias tablas de entre 10% y 15%.

COMPOSITION



	Size	Material	Type of material
Layer 1	0.060-0.070	Varnish	Apresto Mate treatment
Layer 2	3	Hardwood Layer	Quercus spp
Layer 3	9	Intermediate Layer	Wood or HDF slats
Layer 4	2	Contracara	Madera de coníferas


















TOLERANCES

Length of face	± 0.1 %	
Width of face	±0.2 MM	
Squareness of the item	±0.2% de la anchura	
Difference in height among items	±0.2 MM	
Curvature	0.1% of length.	

LABORATORY TESTS

Resistance to abrasion	≥500	UNE-EN 13696:2009*
Mass per surface	10.95 Kg/m2	EN 14342*
Thermal conductivity	0.18 W/M**K	UNE-EN 12667:2002*
Heat resistance	0.08 M2**K/W	UNE-EN 12667:2002*
Formaldehyde emissions	E1	EN 717*
Moisture content	7.00%	UNE-EN 13183-1/AC:2004*
Flammability	Dfl-s1	EN 13501*
Bulk density	782 Kg/m3	UNE-EN 323:1994*
Slip resistance	Clase 2 (35/45)	UNE-CEN/TS 15676:2008*
Biological durability	Clase 1	UNE EN 335 -1 ; UNE EN 335-2*

FEATURES

-  Safety and joint durability are the main features of this easy installation system that guarantees the elimination of gaps between boards throughout the floor's lifetime. The pressure exerted between boards reinforces the union and prevents it from being carried out incorrectly.
-  Applying a color oil or varnish on the wood surface in order to get different color ranges.
-  Slight smoothing of the wood using a brush to achieve a surface with a slight relief.
-  Beveled cut on the long sides of the board in order to create a continuity effect
-  L'ANTIC COLONIAL's varnishing, in two finishes, APRESTO (gloss) and APRESTO MATE (matte), provides a unique surface quality that satisfies the most demanding requirements. Advantages: It achieves the highest cleanliness because, since the pores are seal...
-  Quality product made with selected raw materials, guaranteeing its full residential use for 30 years as provided by L' Antic Colonial.
-  Is suitable for installing on water radiant heating
-  Format where only one board has been used to finish the entire base surface
-  Material with few knots on its surface that can have different sizes depending on the type of wood. These, along with any cracks that may appear, are covered with putty.
-  It is necessary to apply adhesive for installing it.
-  Installation system where gluing the boards to the floor is not necessary. They are installed on a foam and joined together
-  Made with oak wood.
-  There are consistent color changes between pieces.
-  Material from a North American country.
-  Material from a European country.
-  PanEuropean Forest Certification that guarantees to consumers the origin of the products from sustainably managed forests
-  Noble layer

PACKING

Boxes	1.218 M2/CS
Pallets	34.104 M2/PAL
Sale unit	M2
Base unit	ST
Net weight	12.6264 KG/M2
Gross weight	13.2701 KG/M2

SPECIAL PIECES

SAP	KEA	Description	Group	Boxes	Pallet	Units	SKU	Basic Unit	Net weight	Gross weight
100154055	L165003137	IGUALACION TORTONA BORGIO 4,5X270X1,3	G-161	10 ST/CS	1000 ST/PAL	9 ST/M2	ST	ST	1 KG/ST	1 KG/ST
100176604	L165003651	MAMPERLAN TORTONA 1L BORGIO 120X7X3	G-163	2 ST/CS	200 ST/PAL	11 ST/M2	ST	ST	1 KG/ST	1 KG/ST
100154063	L165003142	TRANSICION TORTONA BORGIO 4X270X1,3	G-161	10 ST/CS	1000 ST/PAL	9 ST/M2	ST	ST	1 KG/ST	1 KG/ST
100154067	L165003143	ZOCALO TORTONA BORGIO 8X220X1,4	G-128	12 ST/CS	600 ST/PAL	5 ST/M2	ST	ST	1 KG/ST	1 KG/ST